



TEST REPORT

FL60 Composite Cover BS EN124 Class F900 Load Bearing Test

Document reference number - FIB-FL60-F900-26-06-19

Report by:

M.A.Salisbury
Senior Technician

M. A. Salisbury 

Date test carried out:

26th June 2019

Customer name:

Fibrelite Composites Ltd.
Snaygill Industrial Estate,
Keighley Road,
Skipton,
North Yorkshire
BD23 2QR

Clarifying Statements:

1. The results reported have been performed in accordance with the test requirements agreed by the customer (Fibrelite Ltd.) and laid down in the new BS EN 124-1: 2015 standard along with the composite section EN 124-5.
2. This report does not include or imply any expert opinions as to the serviceability of the sample tested or their suitability for a specific purpose.
3. The submitter disclaims any liability of any kind for any damage whatsoever resulting from the use of either data in the files or the attached values of the test results reported.
4. The report may not be reproduced other than in full, except with the prior written consent of the Engineering Dept., Lancaster University.
5. All testing has been carried out in within the Engineering Department, Gillow Ave., Lancaster University, Bailrigg, Lancaster LA1 4YW.
6. This report applies only to those items and/or materials that have been tested and reported on herein. No inference shall be made to similar test items or materials/ samples.

Cover

The composite cover supplied is a square FL60 complete with aluminium frame. (Photo.1)

Cover No. : 199681

Frame No.: 191256



Photo. 1

Test Rig

The test rig consists of a 'giant mecano' frame bolted to the floor and supporting twin Enerpac 60 ton hydraulic cylinders. (Photo.2)

The cover was seated on steel channels with steel plates and shims to pack and level. A steel box section frame was placed around the aluminium frame to support and for safety.

In accordance with the EN124-1:2015 standard the load cell and test rig complies with EN ISO 7500-1:2004 minimum Class 3.

Test Rig ID: EG100TF

Load Cell ID:

Instron Calibration Certificate No. E225112816155035

System Class: 2



Photo.2

Photograph 3 below shows the calibration certificate for the load cell and test rig.




Photo.3

Test

The tests were carried out in accordance with the EN 124:2015 standard for:

- Permanent Set – Clause 8.2
- Load Bearing Capacity – Clause 8.3

The load was applied to the panel through a 250mm diameter by 45mm thick steel block with a 250mm diameter by 10mm rubber pad between the block and panel.

Permanent Set Test

Measurement of permanent set shall be made on the upper-side of the cover in the same place as the applied load at the longest dimension which can be inscribed within the cover through the centre point of the load application. The measurement device shall be positioned as close as possible to the centre point of the load application and the seating of the measuring device support as close as possible to the edge of the cover but not exceeding 10mm from the edge.

An initial reading is to be taken at the geometric centre of the cover before the first load or any preloading has taken place.

The load is then to be applied at a rate of 1kN/s to 5kN/s up to 2/3 of the test load. This procedure is to be carried out five times without significant disruption.

A final deflection reading shall then be taken and the permanent set determined as the difference of the measured readings between the first and fifth readings.

Load Bearing Capacity

Immediately after the permanent set test the cover shall be loaded up to the test load at a rate of 1kN/s to 5kN/s.

The test load shall then be maintained for 30^{+2}_{-0} seconds.

Results

Permanent set test



Photo.4

Initial Reading	0.00mm
Reading after 5 cycles	0.71mm
Permanent Set	0.71mm

Permissible permanent set for a F900 test is $\frac{CO}{300} = 900/300 = 3.00\text{mm}$

Therefore cover passes the permanent set test.

Load Bearing Capacity Test

Load applied immediately after the permanent set test.

Although the standard does not require it for the load bearing test, a measuring device (linear potentiometer) was placed on the underside of the panel directly under the loading point and deflection readings taken every 600kN for the five cycles and 50kN intervals after that.

LOAD (kN)	DEFLECTION (mm)	REMARKS
0	0.00	
600	11.89	
0	1.64	
600	11.97	
0	1.78	
600	12.04	
0	1.86	
600	12.04	
0	2.01	
600	12.12	
0	2.01	
53	4.09	
100	5.06	
150	5.95	
200	6.69	
250	7.51	
315	8.33	
350	8.92	
400	9.59	
450	10.26	
500	10.85	
550	11.52	
600	12.19	
650	12.86	
700	13.68	
750	14.57	
800	15.61	
850	16.65	
900	17.61	
900 (10 seconds)	17.76	
900 (20 seconds)	17.78	
900 (30 seconds)	17.84	PASS
0	3.12	

The cover held the test load of 900kN for the required 30 seconds with no visible signs of damage, so therefore passed the BS EN 124 Class F900 Load Bearing test.

The slight difference noted between the true permanent set reading taken on the top face and that of the zero readings taken on the underside, can be explained by the cover settling into the frame and supports.

